

# Quality Test Report

ORIGINAL

Test Report No. TW-2360202B

(Page 1 of 1)

Applicant: New Island Printing Group Co., Ltd.

July 17, 2023

Test results to submitted sample are as follows.

Reception Date : June 26, 2023

Item Name : AGS-WB

Number of Item : 1

Test Item : The test of the antiviral efficacy

Test Method : It conformed to ISO21702: 2019

Wash-out solution: SCDLP medium

Test virus : Feline calicivirus ATCC VR-782

Test Result :

Concentration of the test virus:  $3.3 \times 10^7$  PFU/mL

		The common logarithm average of infectivity titer value
Untreated specimens	Immediately after inoculation [ $U_0$ ]	5.91
	After 24 h [ $U_t$ ]	4.62

\* Untreated specimens : Polyethylene film

Test sample	The common logarithm average of infectivity titer value	Antiviral activity value [ $U_t - A_t$ ]
AGS-WB [ $A_t$ ]	3.06	1.5

\*The volume of test inoculum used: 0.4mL The size of the cover film: 16cm<sup>2</sup>

\* This sample was tested on client specified side.

\*Feline calicivirus is used as a replacement for norovirus, since it is a non-enveloped virus with a single-stranded RNA.

\*Tested by Boken Osaka laboratory.

BOKEN QUALITY EVALUATION INSTITUTE  
Taiwan Testing Center

Supervised by

*A. Yamamoto*

Notice - This test result is applied to the submitted sample, not to the lot.  
Unauthorized reproduction, in whole or in part, is strictly prohibited.

