

TEST REPORT

Technical Report: (5222)243-0224

Page 1 of 5 September 15, 2022



BUREAU VERITAS HONG KONG LIMITED 1/F, Pacific Trade Centre, 2 Kai Hing Road Kowloon Bay, Kowloon, Hong Kong Tel: 2331 0888 Fax: 2331 0889 This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/ and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results set fore of based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance ortleria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, you reguligence or if you require measurement uncertaints of the set fills up to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



TEST REPORT

TO: NEW ISLAND PRINTING CO LTD RM1701,17/F BILLION PLAZA 8 CHEUNG YUE STREET CHEUNG SHA WAN KOWLOON, HONG KONG LAB NO.: FORM NO.: DATE IN: DATE OUT: DEPARTMENT: NO. OF WORKING DAYS: PAGE 2 OF 5 (5222)243-0224

/ Aug 31, 2022 Sep 15, 2022 / 11

ATTN : AARON NG

OVERALL RATING
PASS
FAIL
DATA
X

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	1	Factory/Manufacturer:	/
P.O. No.:	1	Style No.:	AGS-WB
Sample Description:	AGS-WB	Style Description:	/
Color:	1	Country of Origin:	/
Claimed Fabric Weight:	1	Claimed Fabric Count:	/
Yarn Size:	1	Submitted Size:	/
Size Range:	1	FPU No.:	/
GPU No.:	1	End Use:	/
Finishing:	1	Age Group:	1
SKU:	/		

Product Category	1
Test Requested	1
Previous Report No.	

Submitted Fiber	1
Content	
Actual Fiber Content	1
Suggested Fiber	/
Content	
Submitted Care	/
Instruction(s)	
Client Expected Care	/
Instruction	
Suggested Care	1
Instruction(s)	



TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
QUANTITATIVE DETERMINATION OF ANTIBACTERIAL FINISHES			Х	

BUREAU VERITAS HONG KONG LIMITED

JEFF CHAN MANAGER SOFTLINES DEPARTMENT



Executive summary

The sample(s) was/were tested to the following standard and the data provided is for informational purposes only.

- AATCC 100-2019: Quantitative Determination of Antibacterial Finishes on Textile Materials

Method Summary

The anti-bacterial properties were evaluated using AATCC 100-2019: Quantitative Determination of Antibacterial Finishes on Textile Materials with the modification of using film to enhance the surface contact.

The following organisms were used for this test: Staphylococcus aureus (ATCC strain no. 6538) and and Escherichia coli (ATCC strain no. 25922).

Test samples were inoculated with the test organisms. After incubation, the bacteria were eluted from the samples by shaking in known amounts of neutralizing solution. The number of bacteria present in this liquid was determined, and the percentage reduction by the treated specimen was calculated.

RESULTS:

Tested Component:

(A) Very pale yellow face side of paper

Percent Reduction (%)		
Name of bacteria used for test	Staphylococcus aureus	Escherichia coli
Percent Reduction (%)	≥ 99.9	≥ 99.9
Comment	For information only	

Recovery of Bacteria		
Name of bacteria used for test	Staphylococcus aureus	Escherichia coli
The number of bacteria recovered from the inoculated treated test specimen swatches immediately after inoculation (at "0" contact time)	149,000	183,000
The number of bacteria recovered from the inoculated treated test specimen swatches incubated over the 24 hours contact period	LT100	LT100
The number of bacteria recovered from the inoculated viability control swatches incubated over the 24 hours contact period	7,000,000	45,000,000

Note:

Percent reduction (%)

100 [(C - A) / C]

GT = Greater Than

LT = Less Than

=

* Identical untreated control sample was not provided

C/N



Remarks:

The criterion for passing the test must be determined by the interested parties.

Information:

Sample size per container:	1 swatch		
Volume of inoculum:	0.4 mL		
Method of sterilization:	None		
No. of bacteria were inoculated per	345,000	cfu/ml of	Staphylococcus aureus
sample:	500,000	cfu/ml of	Escherichia coli
Neutralizing solution:	D/E Neutralizing Broth		
The dilution of the test organism:	1:20 times diluted Trypticase Soy broth with 0.05% Triton X-		ith 0.05% Triton X-100
Plate Count Medium:	Nutrient Agar		
Dimension of test sample:	50 x 50 mm square		
Size of the cover film:	ver film: 60 x 60 mm square, PE material		