

# **TEST REPORT**

**Technical Report:** (5223)034-0117

Page 1 of 5 February 15, 2023





# **TEST REPORT**

TO: NEW ISLAND PRINTING CO LTD RM1701,17/F BILLION PLAZA 8 CHEUNG YUE STREET CHEUNG SHA WAN

KOWLOON, HONG KONG

**ATTN: AARON NG** 

**LAB NO.:** (5223)034-0117 **FORM NO.:** /

**DATE IN:** Feb 03, 2023 **DATE OUT:** Feb 15, 2023

DEPARTMENT: /
NO. OF WORKING DAYS: 7

PAGE 2 OF 5

OVERALL RATING	
PASS FAIL DATA	X

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	AGS-WB
Sample Description:	AGS-WB (SIDE 2)	Style Description:	/
Color:	/	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
Finishing:	/	Age Group:	/
SKU:	/		

Product Category	
Test Requested	1
Previous Report No.	1

Submitted Fiber	
Content	
Actual Fiber Content	
Suggested Fiber	/
Content	
Submitted Care	/
Instruction(s)	
Client Expected Care	/
Instruction	
Suggested Care	/
Instruction(s)	

BUREAU VERITAS HONG KONG LIMITED 1/F, Pacific Trade Centre, 2 Kai Hing Road Kowloon Bay, Kowloon, Hong Kong

Hong Kong Tel: 2331 0888 Fax: 2331 0889 This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/herms-conditions/ and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademant, is permitted only with our prior written permission. This report set sorth our findings solely with respect to the test samples identified herein. The results set forth in this report are not inclicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty, provided. In the complete of any material error or omission caused by our negligence or if you require measurement uncertainty, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
AATCC 100-2019: QUANTITATIVE			X	
DETERMINATION OF ANTIBACTERIAL				
FINISHES ON TEXTILE MATERIALS				

BUREAU VERITAS HONG KONG LIMITED

JEFF CHAN MANAGER SOFTLINES DEPARTMENT

LAB NO: **(5223)034-0117**Page 4 of 5



### **Executive summary**

The sample(s) was/were tested to the following standard and the data provided is for informational purposes only.

- AATCC 100-2019: Quantitative Determination of Antibacterial Finishes on Textile Materials

## **Method Summary**

The anti-bacterial properties were evaluated using AATCC 100-2019: Quantitative Determination of Antibacterial Finishes on Textile Materials with the modification of using film to enhance the surface contact.

The following organisms were used for this test: *Staphylococcus aureus* (ATCC strain no. 6538) and and *Escherichia coli* (ATCC strain no. 25922).

Test samples were inoculated with the test organisms. After incubation, the bacteria were eluted from the samples by shaking in known amounts of neutralizing solution. The number of bacteria present in this liquid was determined, and the percentage reduction by the treated specimen was calculated.

#### **RESULTS:**

**Tested Component:** 

(A)

Rough side of very pale yellow printed paper

Percent Reduction (%)		
Name of bacteria used for test	Staphylococcus aureus	Escherichia coli
Percent Reduction (%)	≥ 99.9	≥ 99.9
Comment	For information only	

Recovery of Bacteria			
Name of bacteria used for test		Staphylococcus aureus	Escherichia coli
The number of bacteria recovered from the inoculated treated test specimen swatches immediately after inoculation (at "0" contact time)	(C)	71,000	109,000
The number of bacteria recovered from the inoculated treated test specimen swatches incubated over the 24 hours contact period	(A)	LT100	LT100
The number of bacteria recovered from the inoculated viability control swatches incubated over the 24 hours contact period		8,500,000	58,000,000

#### Note:

Percent reduction (%) = 100 [(C - A)/C]

GT = Greater Than LT = Less Than

\* Identical untreated control sample was not provided



### Remarks:

The criterion for passing the test must be determined by the interested parties.

### Information:

Sample size per container: 1 swatch

Volume of inoculum: 0.4 mL

Method of sterilization: None

No. of bacteria were 285,000 cfu/ml of Staphylococcus aureus

inoculated per sample: 315,000 cfu/ml of Escherichia coli

Neutralizing solution: D/E Neutralizing Broth

The dilution of the test

organism:

1:20 times diluted Trypticase Soy broth with 0.05% Triton X-100

Plate Count Medium: Nutrient Agar

Dimension of test sample: 50 x 50 mm square

Size of the cover film: 60 x 60 mm square, PE material